Comparison of NaNbO₃ AND NaTaO₃ as the photocatalysts in the reaction of hydrogen generation

Beata Zielińska, Ryszard J. Kaleńczuk

West Pomeranian University of Technology, Szczecin, Institute of Chemical and Environment Engineering, ul. Pułaskiego 10, 70-322 Szczecin, Poland, e-mail: bzielinska@zut.edu.pl

The photocatalytic production of hydrogen over several chemical compounds based on sodium niobates and tantalates has been investigated. The photocatalysts have been prepared by an impregnation method of Nb₂O₅ and Ta₂O₅ in the aqueous solution of sodium hydroxide and then the calcination at the temperature range of 450 – 800°C. In this report, we present the study showing that of the catalysts explored, the highest photocatalytic activity was shown in a sample obtained at the temperature of 450°C and containing NaTaO₃ as a main phase.

Keywords: NaNbO₃, NaTaO₃, photocatalysis, hydrogen generation.

INTRODUCTION

Recently, many studies have been performed to develop heterogeneous photocatalysis for water splitting into hydrogen and oxygen¹⁻³. However, the number of photocatalytic materials found is still limited and the active materials being employed are mainly TiO_2 and titanates. Moreover, the efficiency of photocatalytic hydrogen evolution is relatively low and many photocatalysts will deactivate after a long-term irradiation. Therefore, a development of highly efficient photocatalysts becomes a hot topic in the field of photocatalysis.

NaNbO₃ and NaTaO₃ are well-known perovskite oxides (ABO₃) which possess attractive physical properties such as low density, high sound velocity and are useful for ferroelectric and piezoelectric applications⁴. On the other hand, both of those materials can be candidates as photocatalysts for the reaction of photocatalytic hydrogen generation. Traditionally, NaNbO₃ and NaTaO₃ have been synthesized via solid state reaction of alkali metal carbonates and Nb₂O₅/Ta₂O₅ and the temperature of 800°C or above, which sometimes leads to inhomogenity in composition and coarse particles. Additionally, the problem with preparing alkaline niobates and tantalates is that high temperatures of calcination can lead to the volatilization of alkaline species, resulting in the formation of undesirable secondary phases⁴⁻⁵.

In the current study, the efficiency of $NaNbO_3$ and $NaTaO_3$ used as catalysts in the photocatalytic hydrogen generation will be presented. The photocatalytic reactions were carried out in the presence of formic acid as an electron donor.

EXPERIMENTAL

High purity grade niobium pentaoxide, tantalum pentaoxide (Nb₂O₅, Ta₂O₅, purity 99.99%) and sodium hydroxide (NaOH) supplied by Sigma-Aldrich were used as precursors for the synthesis of sodium niobate and tantalate (NaNbO₃, NaTaO₃). In the first step of the photocatalyst preparation, Nb₂O₅ or Ta₂O₅ were impregnated in the aqueous solution of sodium hydroxide. The molar ratio of Na/Nb₂O₅ and Na/Ta₂O₅ was 2:1. After impregnation, the obtained materials were dried at the temperature of 110°C for 24 hours. The dried materials were

divided into seven equal parts and each of them was calcinated with a certain temperature from the range of between $450 - 800^{\circ}$ C with the step of 50° C. The calcination step at the required temperature was fixed for 11 hours. During the catalysts preparation procedure some amount of NaOH evaporated and in order to keep its concentration at the constant level the additional portion of NaOH solution was introduced into the sample. The excess of the alkali in the samples was washed out with distilled water. The photocatalysts prepared in the abovementioned way are labeled in the following manner: Na/Nb₂O₅-T and Na/Ta₂O₅-T (T means the temperature of calcination).

The crystalline structures of the catalysts were characterized by X-ray diffraction (XRD) analysis (X'Pert PRO Philips diffractometer) using CoK_{α} radiation. The photocatalytic and optical properties of the prepared photocatalysts were investigated by means of Diffuse Reflectance Ultraviolet Visible (DR-UV-vis) technique using a Jasco (Japan) spectrometer. The Planck equation was used for the calculation of the value of the prepared catalysts band gap⁶. The BET surface areas and mean pore diameters of the catalysts were determined by the nitrogen gas adsorption method using a Micrometrics ASAP 2010 device.

The activities of the obtained catalysts for the photocatalytic reactions of hydrogen generation were carried out in a close system with an inner-irradiation-type reactor. As a light source a medium pressure mercury lamp of 150 W was used. The photocatalyst powder was dispersed in an aqueous organic donor solution (0.8 dm³). Formic acid was used as a model organic donor. The suspension was mixed with the magnetic stirrer for 1 hour, and during that time argon was being bubbled through the reaction mixture to remove the oxygen content. Later, the solution was irradiated for two hours without argon purge. The reaction was carried out at a room temperature. The amount of evolved hydrogen was determined by using a gas chromatograph (The Thermal Conductivity Detector (TCD), Ar as a gas carrier).

RESULTS AND DISCUSSION

Fig. 1A and B show the XRD patterns of the catalysts produced after calcination of niobium or tantalum

pentaoxides with sodium hydroxide at different temperature ranges from 450°C to 800°C as well as patterns of the pristine Nb₂O₅ (Fig. 1A) and Ta₂O₅ (Fig. 1B). From Fig. 1A and 1B it is clearly seen that NaNbO₃ and NaTaO₃ phases started to appear at the temperature of 450°C (Na/ Nb₂O₅-450 and Na/Ta₂O₅-450). Additionally, it can be stated that in the case of both those samples the diffraction peaks of Nb₅O₅ and Ta₂O₅ can also be simultaneously detected. Additionally, it can be noticed that when the temperature of calcination increases from 500 to 800°C the intensity of diffraction peaks becomes stronger and NaNbO₃ and NaTaO₃ are the main phase of Na/Nb₂O₅-T and Na/Ta₂O₅-T catalysts, respectively.



Figure 1. A comparison of X-ray diffraction patterns of the pristine Nb_2O_5 (A.) and Ta_2O_5 (B.) and produced Na/Nb_2O_5 -T (A.) and Na/Ta_2O_5 -T (B.) photocatalysts at different temperatures of calcination

The band gap energy (EG) of the pristine Nb₂O₅ and Ta₂O₂ obtained from the optical absorption edge are about 3.07 eV and 3.93 eV, respectively. In the case of Na/Nb₂O₅-T catalysts when the temperature of calcination increases from 450°C to 600°C, band gap energies widely increase from 3.12 eV (Na/Nb₂O₅-450) to 3.45 eV (Na/Nb₂O₅-600). Further increase of the calcination temperature (650 – 800°C) did not cause the change of EG of the

produced materials. Band gap energies of Na/Nb₂O₅-650, Na/Nb₂O₅-700, Na/Nb₂O₅-750 and Na/Nb₂O₅-800 are about 3.45 eV. In the case of Na/Ta₂O₅-T photocatalysts, EG did not change with the increase of the calcination temperature. For all Na/Ta₂O₅-T materials calculated band gap energies equaled about 4.1 eV. Additionally, one can notice that calculated band gap energies of Na/Nb₂O₅-T samples are identical to those described in the literature. The band gap energies of NaNbO₃ and Na/TaO₃ obtained from the optical absorption edge range from 3.08 to 3.5 eV and 3.9 to 4.1 eV, respectively^{6 - 12}.



Figure 2. Band gap energies of Na/Nb₂O₅-T and Na/Ta₂O₅-T photocatalysts

Other characteristic parameters such as BET surface area and a mean pore diameter of the produced photocatalysts (Na/Nb₂O₅-T and Na/Ta₂O₅-T) have also been measured. According to the manufacture's data, Nb₂O₅ and Ta₂O₅ have a small specific surface area of $0.76 \text{ m}^2/\text{g}$ and $1.34 \text{ m}^2/\text{g}$ and a mean pore diameter of 5.25 nm and 10.08 nm, respectively. The comparison of BET surface areas and mean pore diameters of the produced photocatalysts is presented in Fig. 3. We observed that the modification of Nb₂O₅ and Ta₂O₅ with NaOH caused the increase of BET surface areas. For example, BET surface area of Na/Nb₂O₅-450 and Na/Ta₂O₅-450 are about 4.5 and 8 times higher than those of the pristine Nb_2O_5 and Ta₂O₅, respectively. Moreover, from Fig. 4 it is clearly seen that those both parameters decrease with the increase of calcination temperature from 450 to 800°C.

The photocatalytic activities of the obtained materials (Na/Nb₂O₅-T and Na/Ta₂O₅-T) have been studied in the reaction of hydrogen generation. The experiments were conducted in the presence of formic acid as a model organic donor. The concentration of HCOOH (0.1 M) and the weight of the catalyst (0.2g) were kept the same for all reactions. The comparison of hydrogen evolution over the studied photocatalysts is presented in Fig. 4. From the obtained results it is clearly seen that for both Na/Nb₂O₅-T and Na/Ta₂O₅-T photocatalysts the amount of released hydrogen decreases when the calcination temperature increases from 450 to 800°C. For example, the amount of released hydrogen decreases from 80 µmol/h to 41 µmol/h in the case of Na/Nb₂O₅-T catalysts and from 108 µmol/h to 43 µmol/h for Na/Ta₂O₅-T materials. Additionally, it can be state that among all studied



Figure 3. BET surface areas (A.) and mean pore diameters (B.) of Na/Nb₂O₅-T and Na/Ta₂O₅-T photocatalysts

photocatalysts the highest photocatalytic activity was observed for the Na/Ta₂O₅-450. It indicated that the catalyst with the highest surface area (11.63 m²/g, Na/Ta₂O₅-450) exhibited the highest photocatalytic activity.



Figure 4. The photocatalytic hydrogen evolution over Na/ Nb₂O₅-T and Na/Ta₂O₅-T photocatalysts using formic acid solution (HCOOH concentration - 0.1M, amount of catalysts - 0.2 g)

CONCLUSIONS

In summary, sodium niobate and tantalate $(NaNbO_3 and NaTaO_3)$ were synthesized by the impregnation of

 Nb_2O_5/Ta_2O_5 in the aqueous solution of sodium hydroxide and then calcination at the temperature range of 450 – 800°C. The photocatalytic activities of the produced photocatalysts were examined in the reaction of photocatalytic hydrogen generation.

To conclude, among all studied catalysts (niobates and tantalates), the highest photocatalytic activity was observed for the samples named Na/Ta₂O₅-450. The value of 108 μ mol H2/h was detected.

Acknowledgments

This work was sponsored by Polish State Committee for Scientific Research Grant N523 025 32/0983 (B.Z.)

LITERATURE CITED

1. Ni, M., Leung, M.K.H., Leung, D.Y.C. & Sumathy, K. (2007). A review and recent developments in photocatalytic water-splitting using TiO_2 for hydrogen production. *Ren. Sust. Energy Rev.* 11, 401 – 425. DOI:10.1016/j.rser.2005.01.009.

2. Zheng, X.-J., Wei, L.-F., Zhang, Z.-H., Jiang, Q.-J., Wei, Y.-J., Xie, B. & Wei, M.-B. (2009). Research on photocatalytic H_2 production from acetic acid solution by Pt/TiO_2 nanoparticles under UV irradiation. *Int. J. Hydrogen Energy*. 34, 9033 – 9041. DOI:10.1016/j.ijhydene.2009.09.019.

3. Jeong, H., Kim, T., Kim, D. & Kim K. (2006). Hydrogen production by the photocatalytic overall water splitting on $NiO/Sr_3Ti_2O_7$: Effect of preparation method. *Int. J. Hydrogen Energy.* 31, 1142 – 1146. DOI:10.1016/j.ijhydene.2005.10.005.

4. Shanker, V., Samal, S.L., Pradhan, G.K., Narayana, Ch. & Ganguli, A.K. (2009). Nanocrystalline NaNbO₃ and NaTaO₃: Rietveld studies, Raman spectroscopy and dielectric properties. Solid State Sci. 11, 562 – 569. DOI: 10.1016/j.solidstatesciences.2008.08.001.

5. Kato, H., Asakura, K. & Kudo, A. (2003). Highly Efficient Water Splitting into H_2 and O_2 over Lanthanum-Doped NaTaO₃ Photocatalysts with High Crystallinity and Surface Nanostructure. *J. Am. Chem. Soc.* 125, 3082 – 3089.

6. Zielińska, B. & Morawski, A.W. (2005) TiO2 photocatalysts promoted by alkali metals. *Appl. Catal, B*: 55, 221 – 226. DOI:10.1016/j.apcatb.2004.08.015.

7. Liu, J.W., Chen, G., Li, Z.H. & Ahang, Z.G. (2007). Hydrothermal synthesis and photocatalytic properties of ATaO₃ and ANbO₃ (A=Na and K). *Int. J. Hydrogen Energy*. 32, 2269 – 2272. DOI:10.1016/j.ijhydene.2006.10.005.

8. Hsiao, Y.-J., Chang, Y.-H., Chang, Y.-S. Fang, T.-H., Chai, Y.-L., Chen, G.-J. & Huang, T.-H. (2007). Growth and characterization of NaNbO₃ synthesized using reactionsintering method. *Mater. Sci. Eng.* 136, 129 – 133. DOI:10.1016/ j.mseb.2006.09.013.

9. Zhu, H., Zheng, Z., Gao, X., Huang, Y., Yan, Z., Zou, J., Yin, H., Zou, Q., Kable, S. H., Zhao, J., Xi, Y., Martens, W. & Frost R. L. (2006). Structural Evolution in a Hydrothermal Reaction between Nb_2O_5 and NaOH Solution: From Nb_2O_5 Grains to Microporous $Na_2Nb_2O_62/3H_2O$ Fibers and NaNbO₃ Cubes. J. Am. Chem. Soc. 128, 2373 – 2384.

10. Porob, D.G. & Maggard, P.A. (2006). Flux syntheses of La-doped NaTaO₃ and its photocatalytic activity. *J. Solid State Chem.* 179, 1727 – 1732. DOI:10.1016/j.jssc.2006.03.008.

11. Kato, H. & Kudo, A. (1998). New tantalate photocatalysts for water decomposition into H_2 and O_2 . *Chem. Phys. Lett.* 295, 487 – 492.