



A comparison of the traditional casting method and the galvanofforming technique in gold alloy prosthetic restorations

KATARZYNA SARNA-BOS¹, AGATA BATYRA¹, JUSTYNA OLESZEK-LISTOPAD¹,
BEATA PIORKOWSKA-SKRABUCHA¹, JANUSZ BOROWICZ¹, JOLANTA SZYMANSKA^{2*}

¹Department of Prosthetic Dentistry, Medical University of Lublin, Poland

²Chair and Department of Paedodontics, Medical University of Lublin, Karmelicka 7, 20-081 Lublin, Poland

ARTICLE INFO

Received 08 July 2015

Accepted 15 July 2015

Keywords:

gold,
gold alloys,
galvanofforming technique,
biocompatibility,
fixed dentures.

ABSTRACT

Gold is a dental material with very good mechanical properties. It is also aesthetic and biocompatible with the tissues of the oral cavity even at 100% purity. Prosthetic restorations made of pure gold or its alloys can be practiced either through a normal casting, as well as through using the galvanofforming technique. The electrolytic method was first introduced into dentistry about 20 years ago and it allows for producing “pure” gold (which means 99.99% Au). The lack of additions of other metals improves the properties of dental prostheses, such as marginal tightness, esthetics, biocompatibility, and it helps in eliminating any allergic reactions. The literature review presented in this paper is a comparison of the traditional casting method with the newer galvanofforming technique.

INTRODUCTION

The main aim of the contemporary rehabilitation of the stomatognathic system is to make dental prostheses more esthetic, functional and biocompatible. Gold is a material that has been known for hundreds of years and even though technological progress has caused various new materials to appear, gold alloys still remain the best choice. This is due to their biocompatibility with oral cavity tissues. It needs emphasizing that gold is widely used in the dental prosthetics. Removable dentures, where the surface permanently touching the oral cavity tissue, can be made of galvanized gold, as can fixed dentures and even some structures of implant systems [22]. Hence, gold can be considered a universal material, used in all types of dental prostheses [5,9].

There are two basic ways of making gold prosthetic restorations: the traditional casting method and the galvanofforming technique. The electrolytic method was introduced into dentistry about 20 years ago and it allows for processing “pure” gold (which means 99.99% Au) [16]. The lack of other metal additions improves the properties of future prosthetic dentures by improving marginal fit, esthetics, biocompatibility and the elimination of allergic reactions [15,22]. Both methods have their advantages and drawbacks. These should be given a closer look at by researchers.

* Corresponding author

e-mail: szymanska.lublin@gmail.com

tel.: +48 601 165 205

The traditional casting method (lost-wax casting technique)

The lost-wax casting technique is used in dentistry to produce inlays, onlays, overlays, all-metal crowns, porcelain-fused-to-metal crowns and components of partial removable dentures. Casting is a method that allows for making precise copies of a wax pattern of a prosthetic work by changing a wax model into a metal cast. The technique employed is known as the “lost-wax casting process”. The name means that in this process, the wax, which is the model of the cast item, is totally burned away without leaving any residue, and then molten metal alloy (for instance gold alloy) fills this space during the casting process [11].

Laboratory procedures

1. Prepare a cast with a removable die of *high strength dental stone*, and model a previously planned restoration using casting wax:
 - a) prepare the abutment teeth – uncover the preparation margin, isolate it with a layer of spacer lacquer in order to create space (20-35 µm) for the cementation of the final fixed denture on the patient’s tooth [11],
 - b) produce a wax pattern by modeling the tooth in wax (the Adapta Deep Drawing System) or by modeling by way of utilizing a calibrated wax casting
2. Prepare a molding form by attaching sprue and sprue cone to the previously made wax pattern [17].

3. Ensure appropriate preparation of the wax structure for proper contact with the investment material, by covering it with the special substance to increase the surface tension and create a smooth model surface [11].
4. Replace the wax casting with metal alloy using the lost-wax casting technique:
 - a) place a previously prepared wax structure in a casting ring and invest (pour into the mold the investment material). Regarding gold alloys, the employed investment material has a mid melting point (temperature range 700-1200°C). However, other widely available investment materials for both noble and non-noble metals can be utilized [11].
 - b) after the investment material has set, the casting ring should be placed within an oven and heated according to the manufacturer's recommendations: the burn-out process leaves a void that would be filled with the liquid gold alloy [11].
 - c) cast the metal structure – this should be undertaken right after the wax-burning procedure has been accomplished, while the ring is still hot. When casting noble alloys, it is recommended to use a crucible former with a graphite addition so as to heat up only a particular amount of the alloy. Note: if the metal alloy is not sufficiently heated, it may not fill in the form totally. On the other hand, if it has been heated up too much, it might cause the investment material to crack.
5. Cooling – Polak suggests that the ring should be cooled slowly – by being kept in a hot oven [17]. Other authors suggest that it need only be cooled at room temperature or in a heated bath. Cooling the form too quickly might lead to deterioration of its properties, particularly, its endurance [26]. Free the cast metal structure from the investment material. Subsequently, the metal form should be cleaned using a sandblasting machine (particles of aluminum oxide with the diameter of 110-125 µm and 2-bar pressure) and then placed in an acid bath for 5 to 10 seconds (sulphuric acid solution).
6. Seat the cast metal structure on the die and mechanically prepare the casting. The marginal fit of a prosthetic restoration made with the traditional casting technique ranges between 50 and 120 µm [8,10]. At this stage, sprue and the sprue cone are cut off. One of the disadvantages of this traditional method of casting is that the residue of the alloy (sprue and sprue cone) cannot be used again, which means that about 25% of the material is lost [19].
7. Remove the excess metal, thus forming the final shape of the structure. Eventually, it will also be sandblasted again, using an aluminum oxide, and then polished. Following this, it will be delivered to a dentist for a try-on procedure [11].

Galvanofarming

The galvanofarming technique was invented in 1961, in Australia. It is based on the process of electrolysis [18]. The monometal (99.5-99.9% Au) produced in the process is resistant to thermal, chemical and mechanical factors. Hence, the corrosion risk that the alloy additions might cause is eliminated [10,21,26]. Furthermore, galvanized 24-carat gold has much better biological and physicochemical

properties than cast gold alloys. This technique is most commonly used to make inlays, onlays, overlays, crowns, short-span bridges, telescoping crowns and implant-supported fixed dentures [2,4,23].

Laboratory procedures

1. Prepare the cast by way of utilizing a removable die of *high strength dental stone* and correct potential undercuts or porosity in the region of the removable die [21].
2. Isolate and cover the layer of the prepared die with spacer lacquer [13].
3. Fabricate a duplicate out of epoxy-resin die (deemed the 'duplicated micromodel') [13].
4. Place a copper brad (a cathode) on the die under the tooth preparation margin and coat the die with a thin layer of silver lacquer to enable electrical conductivity [1,8].
5. Immerse the duplicate die in a galvanizing bath containing electrolyte and ammonium gold sulphite [8].
6. Set out proper parameters for the process: utilize the recommended electric current intensity, the appropriate bath temperature, as well as the suitable time interval. This last is dependent on the desired thickness of the metal structure. For instance, within a 10 hours, 0.2 mm of gold is laid down. During a 1 second interval, about 30 billion gold atoms appear on the cathode's surface [21].
7. Complete the galvanization process, rinse the die, remove the gold structure and rinse this as well [13].
8. Remove the residue of the lacquer through the process of sandblasting, using aluminum oxide powder, and then etch it by way of employing a solution of nitrogenous acid (50%), subsequently, fit the gold cup [13].
9. Prepare the gold substructure for ceramic veneering.
 - a) sandblast the substructure surface with corundum sand (50 µm diameter) under 1.5 bar pressure and clean it using hot water steam (stream abrasion technique)
 - b) Note: there is no surface enabling a chemical bonding of metal with ceramics which means that a special bond (pure Au with ceramics) needs to be applied twice. This action improves the strength of the bonding between the gold substructure and the ceramics. Moreover, it becomes the intermediate layer between two phases during the burning process [13,21].

Discussion

The galvanofarming technology allows for obtaining particular prosthetic restoration elements of very regular and fine-grained structure. This makes them much more resistant to fractures or mechanical impact. These advantages enable dentists to make thin-walled dentures (around 0.2 mm) whilst keeping a high level of precision and hardness [5,19]. Furthermore, it makes for very efficient preparation of the hard tooth tissue, and this translates into better esthetic effect in the case of the final prosthetic restoration. The high marginal fit of the gold substructure (about 20 µm) is also its advantage [24,26].

The traditional metal casting technique has a range of advantages as well. One of these is that there is a layer of oxides established that provides a stable connection with the veneering ceramics and brings about higher endurance against fracture, in comparison with the galvanofarming

technique. A comparison of prosthetic fillings made by the traditional casting process and by the galvanofforming technique is presented in Table 1.

Table 1. A comparison of gold prosthetic restorations made by the traditional casting method and by galvanofforming

Feature	Traditional casting method	Galvanoforming technique
Degree of purity	lower, possible dirt from the crucible	higher
Material consumption	higher	lower
Thickness	even 0.5 mm	0.2-0.4 mm
Weight	1.0 g at minimum	about 0.5 g
Porcelain mass: metal thickness ratio	4:1	1.7:1
The size of grains in the internal structure	400 μm	50 μm
Hardness	25-28 HV	100-150 HV
Surface of metal oxides	present	absent
Dental plaque formation	more frequent	less frequent
Color	white-gold	gold
Porcelain discoloration	possible (depends on the alloy parts)	possible only when the oven was dirty
Marginal fit	50-120 μm , up to 200 μm	20 μm
Biocompatibility	depends on the alloy	almost 100%
Fracture resistance	higher	lower
Preparation of tooth tissues	higher	lower
Amount of dental technician's work	high	low
Costs	lower	higher

Making prosthetic restorations by way of the galvanofforming technique requires the use of specialist devices (electrolyte baths, microprocessing units), reagents and other supplementary materials. The necessity of these obviously boosts the costs of the whole procedure, at least when compared with the traditional casting method. At the moment, the galvanization process itself is conducted using digitally-controlled devices [10]. In the case of the traditional casting method, only items common to the jewelry business are needed.

Galvanoforming allows for obtaining completely “pure” structures. The crucibles and compounds used in the traditional technique may cause an increase in contamination, the amount of which goes up every time the crucible is used. Moreover, employing the galvanofforming technique means a forty percent lower consumption of gold – which translates into huge material savings [8]. In addition, there is no contamination – which positively affects the rates of allergization [15,22].

Galvanized structures are thin-walled and their thickness or weight are much reduced. One crown weighs about 0.5 g, whilst with regard to the traditional casting method, it would be 1.0 g [19]. Low thickness is another advantage of a golden substructure (0.2-0.4 mm), which translates into much more space for the veneering material (even 1.0 mm) [10]. For comparison, the thickness of a substructure made of golden alloys should be 0.5 mm at least [21].

A substructure produced by way of the galvanofforming technique is tantamount to generating a much better visual effect, as well as having more profound colors [15]. The ratio of porcelain to the thickness of the metal structure of a crown is 1.7:1, whilst in case of galvanized prosthetic restorations, it is 4:1 [6,7,14]. This means that there is a possibility of a much more efficient preparation of the tooth

tissues [21]. This is extremely important with regard to crowns made for smaller teeth, such as mandibular incisors, for instance [8].

Galvanized gold has a uniform structure with ordered grains (about 50 μm), whilst in the case of traditional casting of prosthetic restorations, the rate can be almost 80% higher, reaching 400 μm . Furthermore, using the traditional technique might create some contraction cavities or empty spaces without metal. This phenomenon is not present in restorations made by way of the galvanofforming technique [10,17].

The internal structure of any item influences its hardness, which means that the regular crystal structure of galvanized gold is even four times harder than in the situation of gold processed by way of the traditional casting method [19,25]. Using the Vickers’ scale, it is 100-150 HV and 25-28 HV, respectively [1,21].

Oxides tend to appear on the surface of the structures made as a result of galvanofforming. This improves the connection between the metal and the ceramic components [26]. If they are absent, it is necessary to use special bonding agents and bonding constructions that connect the ceramic with gold in a micromechanical retention [1,8,10]. At the same time, the lack of new ions can eliminate its deteriorating influence on the periodontium. Clinical observations have demonstrated that minimal deposition of dental plaque on the galvanized structures allows for keeping marginal gingiva in good condition [10].

The esthetic factor is a significant advantage shared by both methods. The metallic shine of the subgingival area is eliminated by the warm color of gold [3,20,24]. Moreover, various alloying additions can change the color of the structure. In the case of the galvanofforming method, this usually generates a warm golden color. Beyond this, firing porcelain onto gold, can bring about slight changes in color. This might happen when a gold alloy (which contains copper or silver) is used. When the foundation is made using the galvanized method, the color can only change because of some contamination being present in the porcelain firing (copper fumes, for instance) [26].

Relatively high (up to 20 μm) marginal fit in galvanized prosthetic restorations is yet another advantage [6,7,14,22]. This provides great protection against failing dental cement, caries creation or inflammations of the periodontium. High tightness is also required in the case of undertaking more precise work, such as fabricating telescopic crowns. According to different sources, full gold crowns are much worse when it comes to marginal fit – mainly to 50-120 μm [1], and sometimes even to 200 μm [6,7,14].

During the galvanization process, 24-carat gold structures are produced, which means they are 100% biocompatible [1,2]. They have much better physicochemical or biological properties than those made of gold alloys, where corrosion resistance may be different and dependent on the amount of the non-noble metals inside [2,3,12,20,24]. However, prosthetic restorations made of gold alloys (formed by way of the traditional casting method) are much more resistant to fractures, hence, they are regularly employed in long-span dental bridges procedures [19].

Finally, the traditional casting method takes much more work and effort in order to generate a useful product. The laboratory procedures consist of numerous stages and there is less automation than in the case of the galvanofforming technique [19,26] (Tab. 1).

CONCLUSION

Prosthetic restorations made of pure gold through the galvanofforming process are much better than those made with the traditional casting method. However, the high price of material and the fact that the restorations require some special devices to be used remain to be the main obstacles.

REFERENCES

1. Biały M., Dąbrowa T., Więckiewicz W.: Galwanofforming jako alternatywa dla złożonych uzupełnień protetycznych. *Dent. Forum*, 41, 69, 2013.
2. Biewer P.: Development of the G.E.S. electroforming technique: biocompatible, corrosion-free production of telescopic crowns. *J. Dent. Technol.*, 16, 24, 1999.
3. Biewer P.: Galvanosekundark ronnen sind in der Passung unschlagbar. *DZW*, 8, 18, 2000.
4. Ernst K. K.: Uzupełnienia złote. Wykonanie galwanicznej protezy teleskopowej. *Quintessence. Dent. Technol.*, 9, 7, 2004.
5. Gnadlinger K.: Legierung: Komposit und Keramik-alles passt zusammen. *DZW SPEZIAL – Legierungen*, 1, 45, 1999.
6. Hammerle C. H., Mesaric W., Lang N. P.: Marginal fit of porcelain crowns with galvanized frames. *Schweiz Monatsschr Zahnmed*, 104, 740, 1994.
7. Holmes J. R., et al.: Marginal fit of electroformed ceramometal crowns. *Int. J. Prosthodont.*, 5, 111, 1996.
8. Jedynak B., Szczyrek P.: Zastosowanie techniki galwanofformingu w protetyce stomatologicznej. *Protet. Stomatol.*, 60, 32, 2010.
9. Koch J.H., Fuming A.: Presskeramik: Die Krone von Funktionen und Asthetik. *Zahnarzt & Praxis*, 1, 14, 2002.
10. Majewski S.: Nowe technologie wytwarzania stałych uzupełnień zębów: galwanofforming, technologia CAD-CAM, obróbka tytanu i współczesne systemy ceramiczne. *Protet. Stomatol.*, 57, 125, 2007.
11. Oidak W.: Wykonanie estetycznej protezy stałej – mostu okrężnego. Etapy postępowania – cz. II. *Nowocz. Tech. Dentyst.*, 4, 9, 2005.
12. Otulakowska-Skrzyńska J., Krysiński Z.: Korozja biologiczna metalicznych materiałów dentystycznych w środowisku jamy ustnej. *Implantoprotet.*, 5, 16, 2004.
13. Pawłowski W.: Wykonanie estetycznego uzupełnienia w przednim odcinku górnego łuku zębów na podbudowie ze złota galwanicznego. *Nowocz. Tech. Dentyst.*, 2, 10, 2006.
14. Petteno D., et al.: Comparison of marginal fit of 3 different metal-ceramic systems: an in vitro study. *Int. J. Prosthodont.*, 13, 405, 2000.
15. Pietruska M., Pietruski J.: Zastosowanie techniki galwanofformingu w protetyce. *Protet. Stomatol.*, 54, 352, 2004.
16. Pietruski J.K., Pietruska M.D.: Materiały i technologie używane we współczesnej protetyce stałych uzupełnień zębów – wady i zalety przedstawione na podstawie przeglądu piśmiennictwa i doświadczeń własnych. *Stomatol. Estet.*, 9, 89, 2013.
17. Polak A.: Teoretyczne podstawy i praktyczne wskazówki z zakresu odlewnictwa. *Nowocz. Tech. Dentyst.*, 2, 28, 2005.
18. Rogers O. W., Armstrong B. W.: Electroforming a gold matrix for indirect inlays. *J. Prosthet. Dent.*, 11, 959, 1961.
19. Rosak P., et al.: Galwanofforming a tradycyjny odlew. *Nowocz. Tech. Dentyst.*, 5, 42, 2011.
20. Schuler Dental: Sparsames Feinstrahlgerät, biologisch abbaubare Gussmuffel-Einlage und biokompatible Vergoldungselektrolyte. *DZW Zahn Technik*, 5, 37, 1999.
21. Stwora I., Zieliński K., Kokot T.: Technika galwanofformingu w protetyce stomatologicznej. *Nowocz. Tech. Dentyst.*, 6, 52, 2010.
22. Tejchman H., Bogurski M., Nawrocki M.: Możliwości zastosowania techniki galwanicznej w stomatologii – obserwacje wstępne. *Protet. Stomatol.*, 52, 291, 2002.
23. Tietmann C., Broseler F.: Enhanced periodontal response and esthetics of implant – supported bridge by the use of galvanofforming technique: case report. *Clin. Implant. Dent. Relat. Res.*, 4, 53, 2002.
24. Wagner R.: Speziell zum System gehorende optimierte Legierung neu auf dem Markt. *DZW Zahn Technik*, 11, 32, 2000.
25. Vence B. S.: Electroforming technology for galvanoceramic restorations. *J. Prosthet. Dent.*, 77, 444, 1997.
26. Zielińska A., Wojtczak A., Suchorzewski A.: Stałe uzupełnienia protetyczne na podbudowie ze złota – porównanie galwanofformingu z metodą tradycyjnego odlewu. *Dent. Forum*, 35, 59, 2007.